


# MACKINTOSH® AIR TASLAN 3L

100% PP

190gsm | WovenOxford

Fabric Name:	MACKINTOSH® AIR TASLAN 3L
Model:	P034
Color:	Orange
Denier:	81D
Fabric Weight:	190gsm
Composition:	100% PP
Width:	60
Weave:	WovenOxford
Application:	Outdoor Sportswear: Jackets, Pants
Warp:	81D FDY
Weft:	85D ATY (-> 120D ATY)



## Product Characteristics

Test Description	Protocol	Results
Dimensional Stability to Washing	ISO 3759-2011	TBD
Abrasion Resistance	ISO 12947-2	40000
Pilling Resistance	ASTM D4970   ISO 12945-2	7000   7000
Tear Strength Warp/Weft	ASTM D2261	N/A
Color Fastness to Washing	ISO105-C06	TBD
Color Fastness to Rubbing	ISO105-X12	TBD
Color Fastness to Light	ISO105-B02	TBD
Rain Test	AATCC 35	TBD
Spray Test	AATCC 22	90<>100
Water Repellency	ISO 4920	4
Water Repellency After Wash	ISO 9865/6330	3
Hydrostatic Head Pressure (Before/After Wash)	AATCC 127	38320   35210
Hydrostatic Head Pressure (Before/After Wash)	JIS L 1092	38320   35210
Bundesmann Average Water Absorption	ISO 9865	12.5%
Bundesmann Average Visual Grade	ISO 9865	3
Bundesmann Wetting to Underside	ISO 9865	No
Bundesmann Average Penetration	ISO 9865	0

HIGG MSI			CO2 Emissions (CO2e/kg)	3L: 11.669
Global Warming	Eutrophication	Water Scarcity	Resource Depletion	Chemistry
TBD	TBD	TBD	TBD	TBD

[www.axroma.com](http://www.axroma.com)

TAIWAN AXROMA TECHNICAL TEXTILES CO., LTD.  
No. 636 Hsi-Ping Road, Douliou City  
Yunlin Hsien, 64057, Taiwan  
T: 886-5-5511008 F: 886-5-5511010

AXROMA TECHNICAL TEXTILES (LIANYUNGANG) CO., LTD.  
No. 25 YuZhou Road (South), Haizhou Development Zone  
Lianyungang City, JiangSu Province 222062 China  
T: 86-518-85910058 F: 86-518-85910057